

Bibliographic Fields

Document Identity

(19)【発行国】

日本国特許庁(JP)

(12)【公報種別】

公開特許公報

(11)【公開番号】

特開 2004-059535(P2004-059535A)

(43)【公開日】

2004-02-26

(19) [Publication Office]

Japan Patent Office (JP)

(12) [Kind of Document]

Japan Unexamined Patent Publication

(11) [Publication Number of Unexamined Application]

Japan Unexamined Patent Publication 200 4- 059535 (P200 4-059535A)

(43) [Publication Date of Unexamined Application]

2,004 - 2 - 26

Public Availability

(43)【公開日】

2004-02-26

(43) [Publication Date of Unexamined Application]

2,004 - 2 - 26

Technical

(54)【発明の名称】

アントラセン誘導体、有機エレクトロルミネッセンス素子用発光材料及び有機エレクトロルミネッセンス素子

(54) [Title of Invention]

LIGHT-EMITTING MATERIAL AND ORGANIC ELECTROLUMINESCENT ELEMENT FOR ANTHRACENE DERIVATIVE、ORGANIC ELECTROLUMINESCENT ELEMENT

(51)【国際特許分類第 7 版】

C07C13/58

C07C13/615

C07C15/60

C09K11/06

H05B33/14

H05B33/22

【FI】

C07C13/58

C07C13/615

C07C15/60

C09K11/06 610

C09K11/06 635

C09K11/06 645

C09K11/06 650

C09K11/06 655

(51) [International Patent Classification, 7th Edition]

C07C13/58

C07C13/615

C07C15/60

C09K11/06

H05B33/14

H05B33/22

[FI]

C07C13/58

C07C13/615

C07C15/60

C09K11/06 610

C09K11/06 635

C09K11/06 645

C09K11/06 650

C09K11/06 655

JP2004059535A

2004-02-26

C09K11/06 690

C09K11/06 690

H05B33/14 B

H05B33/14 B

H05B33/22 B

H05B33/22 B

H05B33/22 D

H05B33/22 D

【テーマコード(参考)】

[Theme Code (For Reference)]

3K007

3 K007

4H006

4 H006

【Fターム(参考)】

[F Term (For Reference)]

3K007AB02

3 K007AB02

3K007AB03

3 K007AB03

3K007AB06

3 K007AB06

3K007DB03

3 K007DB03

4H006AA01

4 H006AA01

4H006AA03

4 H006AA03

4H006AB91

4 H006AB91

【請求項の数】

[Number of Claims]

7

7

【出願形態】

[Form of Application]

OL

OL

【全頁数】

[Number of Pages in Document]

26

26

Filing

【審査請求】

[Request for Examination]

未請求

Unrequested

(21)【出願番号】

(21) [Application Number]

特願 2002-222990(P2002-222990)

Japan Patent Application 200 2- 222990 (P200 2- 222990)

(22)【出願日】

(22) [Application Date]

2002-07-31

2,002 - 07 - 31

Parties

Applicants

(71)【出願人】

(71) [Applicant]

【識別番号】

[Identification Number]

000183646

000183646

【氏名又は名称】

[Name]

出光興産株式会社

IDEMITSU KOSAN CO. LTD. (DB 69-054-8839)

【住所又は居所】

東京都千代田区丸の内3丁目1番1号

Inventors

(72)【発明者】

【氏名】

池田 秀嗣

【住所又は居所】

千葉県袖ヶ浦市上泉1280番地

(72)【発明者】

【氏名】

井戸 元久

【住所又は居所】

千葉県袖ヶ浦市上泉1280番地

(72)【発明者】

【氏名】

舟橋 正和

【住所又は居所】

千葉県袖ヶ浦市上泉1280番地

(72)【発明者】

【氏名】

東海林 弘

【住所又は居所】

千葉県袖ヶ浦市上泉1280番地

Agents

(74)【代理人】

【識別番号】

100078732

【弁理士】

【氏名又は名称】

大谷 保

Abstract

【課題】

低電圧でありながら高い発光輝度及び効率が得られ、有機EL素子の消費電力の低減が可能な有機EL素子、それを実現するアントラセン誘導体及び有機EL素子用発光材料を提供する。

[Address]

Tokyo Prefecture Chiyoda-ku Marunouchi 3-1-1

(72) [Inventor]

[Name]

Ikeda Hidetsugu

[Address]

Chiba Prefecture Sodegaura City Kamiizumi No.1280

(72) [Inventor]

[Name]

well Motohisa

[Address]

Chiba Prefecture Sodegaura City Kamiizumi No.1280

(72) [Inventor]

[Name]

Funabashi Masakazu

[Address]

Chiba Prefecture Sodegaura City Kamiizumi No.1280

(72) [Inventor]

[Name]

Tokairin Hiroshi

[Address]

Chiba Prefecture Sodegaura City Kamiizumi No.1280

(74) [Attorney(s) Representing All Applicants]

[Identification Number]

100078732

[Patent Attorney]

[Name]

Otani preservation

[Problems to be Solved by the Invention]

With low voltage high light emitting brightness and efficiency are acquired, anthracene derivative and light-emitting material for organic EL device which actualize organic EL device, that decrease of the electricity consumption of organic EL device is possible are offered


【解決手段】

式(1)で表されるアントラセン誘導体及び該誘導体からなる有機EL素子用発光材料、並びに陰極と陽極間に少なくとも発光層を含む一層又は複数層からなる有機薄膜層が挟持されている有機EL素子において、該有機薄膜層の少なくとも1層が、前記アントラセン誘導体を単独もしくは混合物の成分として含有する有機EL素子である。

device is possible are offered.

[Means to Solve the Problems]

At least 1 layer of said organic thin film layer, is organic EL device which contains theaforementioned anthracene derivative as component of alone or mixture organic thin film layer which consists of one layer or multiple layers which at least includes light emitting layer between the light-emitting material, and cathode and anode which for organic EL device consist of the anthracene derivative and said derivative being displayed with Formula (1) in organic EL device which clamping is done.



(Xは、ハロゲン置換もしくは無置換のアルキル基、アリール基、アルキル基等、Arは置換もしくは無置換の縮合アリール基、Ar'は置換もしくは無置換のアリール基で、a及びbは0～4、aとbは同時に0にはならず、nは1～3である。)

(As for X, as for Ar such as halogen substituted or alkyl group, aryl group, alkyl group of nonsubstitution as for substituted or unsubstituted condensed aryl group, Ar' with substituted or unsubstituted aryl group, as for a and b 0 - 4, as for a and b it does not become simultaneously 0, n is 1 - 3.)

【選択図】

なし

{selected drawing }

none

Claims

【特許請求の範囲】

【請求項 1】

下記一般式(1)で表されるアントラセン誘導体。

[Claim(s)]

[Claim 1]

anthracene derivative. which is displayed with below-mentioned General Formula (1)

【請求項 2】

[Claim 2]

【請求項 3】

[Claim 3]

請求項1に記載のアントラセン誘導体からなる有機エレクトロルミネッセンス素子用発光材料。

light-emitting material. for organic electroluminescent element which consists of anthracene derivative which is stated in Claim 1

【請求項 4】

[Claim 4]

陰極と陽極間に少なくとも発光層を含む一層又は複数層からなる有機薄膜層が挟持されている有機エレクトロルミネッセンス素子において、該有機薄膜層の少なくとも1層が、請求項3に

organic electroluminescent element. which contains light-emitting material for organic electroluminescent element which said organic thin film layer 1 layer, states at least in Claim 3 organic thin film layer which consists of the one

記載の有機エレクトロルミネッセンス素子用発光材料を単独もしくは混合物の成分として含有する有機エレクトロルミネッセンス素子。

【請求項 5】

前記有機薄膜層が、電子輸送層及び／又は正孔輸送層を有し、該電子輸送層及び／又は正孔輸送層が、請求項3に記載の有機エレクトロルミネッセンス素子用発光材料を単独もしくは混合物の成分として含有する有機エレクトロルミネッセンス素子。

【請求項 6】

前記発光層が、さらにアリアルアミン化合物を含有する請求項4又は5に記載の有機エレクトロルミネッセンス素子。

【請求項 7】

前記発光層が、さらにスチリルアミン化合物を含有する請求項4又は5に記載の有機エレクトロルミネッセンス素子。

Specification

【発明の詳細な説明】

【0001】

【発明の属する技術分野】

本発明は、アントラセン誘導体、有機エレクトロルミネッセンス素子用発光材料及び有機エレクトロルミネッセンス素子に関し、さらに詳しくは、低電圧でも発光輝度及び発光効率が高い有機エレクトロルミネッセンス素子、それを実現するアントラセン誘導体及び有機エレクトロルミネッセンス素子用発光材料に関するものである。

【0002】

【従来の技術】

有機エレクトロルミネッセンス素子(以下エレクトロルミネッセンスをELと略記することがある)は、電界を印加することより、陽極より注入された正孔と陰極より注入された電子の再結合エネルギーにより蛍光性物質が発光する原理を利用した自発光素子である。

イーストマン・コダック社のC. W. Tangらによる積層型素子による低電圧駆動有機EL素子の報告(C. W. Tang, S. A. Vanslyke, アプライドフィジックスレターズ(Applied Physics Letters), 51巻、913頁、1987年等)がなされ

layer or multiple layers which at least includes light emitting layer between cathode and the anode in organic electroluminescent element which clamping is done, as component of alone or mixture

[Claim 5]

organic electroluminescent element, which contains light-emitting material for organic electroluminescent element where the aforementioned organic thin film layer, has electron transporting layer and/or hole transporting layer, said electron transporting layer and/or hole transporting layer, states in Claim 3 as component of alone or mixture

[Claim 6]

Aforementioned light emitting layer, furthermore organic electroluminescent element, which is stated in the Claim 4 or 5 which contains aryl amine compound

[Claim 7]

Aforementioned light emitting layer, furthermore organic electroluminescent element, which is stated in the Claim 4 or 5 which contains styryl amine compound

[Description of the Invention]

{0001}

[Technological Field of Invention]

this invention regards light-emitting material and organic electroluminescent element for anthracene derivative, organic electroluminescent element, furthermore details are something regarding anthracene derivative and light-emitting material for organic electroluminescent element which actualize organic electroluminescent element, that light emitting brightness and light emission efficiency are high even with low voltage.

{0002}

[Prior Art]

As for organic electroluminescent element (EL briefly describes below electroluminescence is.), fluorescence substance is spontaneous light emission element which utilizes the principle which light emitting is done from fact that imparting it does the electric field, from anode with recombination energy of electron which was filled from positive hole and cathode which were filled.

Since with C.W.Tang and others of Eastman * Kodak corporation doing thereport (C.W. Tang, S.A. Vanslyke, Applied physics letters (Applied Physics Letters), Vol.51, 913 page, 1987 etc) of low voltage drive organic EL device with laminated type element, research regarding the organic

て以来、有機材料を構成材料とする有機EL素子に関する研究が盛んに行われている。

Tangらは、トリス(8-ヒドロキシキノリノールアルミニウム)を発光層に、トリフェニルジアミン誘導体を正孔輸送層に用いている。

積層構造の利点としては、発光層への正孔の注入効率を高めること、陰極より注入された電子をブロックして再結合により生成する励起子の生成効率を高めること、発光層内で生成した励起子を閉じ込めること等が挙げられる。

この例のように有機EL素子の素子構造としては、正孔輸送(注入)層、電子輸送発光層の2層型、または正孔輸送(注入)層、発光層、電子輸送(注入)層の3層型等がよく知られている。

こうした積層型構造素子では注入された正孔と電子の再結合効率を高めるため、素子構造や形成方法の工夫がなされている。

【0003】

また、発光材料としてはトリス(8-キノリノラート)アルミニウム錯体等のキレート錯体、クマリン誘導体、テトラフェニルプタジエン誘導体、ビススチリルアリーレン誘導体、オキサジアゾール誘導体等の発光材料が知られており、それらからは青色から赤色までの可視領域の発光が得られることが報告されており、カラー表示素子の実現が期待されている(例えば、特開平8-239655号公報、特開平7-138561号公報、特開平3-200289号公報等)。

また、発光材料としてフェニルアントラセン誘導体を用いた素子が特開平8-012600号公報に開示されている。

このようなアントラセン誘導体は青色発光材料として用いられるが、素子寿命を伸ばすように薄膜の安定性が求められていた。

しかしながら、従来のモノアントラセン誘導体は結晶化し薄膜が破壊される場合が多く改善が求められていた。

例えば、米国特許05935721号明細書にはジナフチルアントラセン化合物が開示されている。

しかし、この化合物は、電荷注入がしにくく駆動電圧が高電圧であり、消費電力を低減する観点から駆動電圧を小さくすることが求められていた。

EL device which designates organic material as constituent material is done actively.

Tang and others, tris (8 -hydroxy quinolinol aluminum) in light emitting layer, has used triphenyl diamine derivative for hole transporting layer.

As benefit of laminated structure, injection efficiency of positive hole to light emitting layer is raised, block doing electron which was filled from cathode, you can list fact that etc it shuts in exciton which raises the production efficiency of exciton which it forms with recombination forms inside the light emitting layer.

Like this example positive hole transport (Fill) layer, three-layer type etc of 2 layers types, or positive hole transport (Fill) layer and light emitting layer, electron transport (Fill) layer of electron transport light emitting layer is well known as the element structure of organic EL device.

In order with such laminated type constituent child to raise recombination efficiency of the positive hole and electron which were filled, device of element structure and the formation method has done.

{0003}

In addition, tris (8 -quinolinolato) aluminum complex or other chelate complex, coumarin derivative, tetra phenyl butadiene derivative, bisstyryl arylene derivative, oxadiazole derivative or other light-emitting material is known as light-emitting material, from those the light emitting of visible region to red color is acquired from blue to be reported, actualization of color display element is expected, (for example Japan Unexamined Patent Publication Hei 8 - 239655 disclosure, Japan Unexamined Patent Publication Hei 7 - 138561 disclosure, Japan Unexamined Patent Publication Hei 3 - 200289 disclosure etc).

In addition, element which uses phenyl anthracene derivative as light-emitting material is disclosed in Japan Unexamined Patent Publication Hei 8 - 012600 disclosure.

As for this kind of anthracene derivative it is used as blue light-emitting material, but in order to extend element lifetime, stability of thin film was sought.

But, crystallization it did conventional mono anthracene derivative and when thin film is destroyed improvement it was sought mainly.

dinaphthyl anthracene compound is disclosed in for example U.S. Patent 05935721 specification .

But, this compound, charge fill to be difficult to do drive voltage being the high voltage , makes drive voltage small from viewpoint which decreases electricity consumption, it was sought .

さらに結晶化を抑制する必要があった。

【0004】

【発明が解決しようとする課題】

本発明は、前記の課題を解決するためなされたもので、低電圧でありながら高い発光輝度及び効率が得られ、有機EL素子の消費電力の低減が可能な有機EL素子、それを実現するアントラセン誘導体及び有機EL素子用発光材料を提供することを目的とする。

【0005】

【課題を解決するための手段】

本発明者らは、前記目的を達成するために、鋭意研究を重ねた結果、下記一般式(I)で表される特定のアントラセン構造を有する化合物を有機EL素子の発光材料として用いると、置換基Xの立体障害基としての効果により分子間の会合が抑制され、高発光輝度及び効率でありながら、駆動電圧を低電圧化することができる上、素子寿命も長いことを見出し、本発明を完成するに至った。

【0006】

すなわち、本発明は、下記一般式(1)で表されるアントラセン誘導体、該アントラセン誘導体からなる有機EL素子用発光材料を提供するものである。

【化4】

(式中、Xは、ハロゲン原子、ヒドロキシル基、ニトロ基、シアノ基、置換もしくは無置換の炭素数1～50のアルキル基、置換もしくは無置換の核炭素数6～50のアリール基、置換もしくは無置換の炭素数5～50のシクロアルキル基、置換もしくは無置換の炭素数1～50のアルコキシ基、置換もしくは無置換の核原子数5～50の芳香族複素環基、置換もしくは無置換の炭素数1～50のアラルキル基、置換もしくは無置換の核炭素数6～50のアリールオキシ基、置換もしくは無置換の核炭素数6～50のアリールチオ基、置換もしくは無置換の炭素数1～50のアルコキシカルボニル基、又はカルボキシル基を表し、Xのうち少なくとも1つは、置換もしくは無置換の核炭素数6～50のアリール基、置換もしくは無置換の炭素数5～50のシクロアルキル基、置換もしくは無置換の核原子数5～50の芳香族複素環基、置換もしくは無置換の炭素数1～50のアラルキル基、置換もしくは無置換の核炭素数6～50のアリールオキシ基、置換もしくは無

Furthermore it was necessary to control crystallization.

{0004}

[Problems to be Solved by the Invention]

As for this invention, in order to solve aforementioned problem, being something which it is possible, with low voltage high light emitting brightness and efficiency are acquired, anthracene derivative and light-emitting material for organic EL device which actualize organic EL device, that decrease of electricity consumption of organic EL device is possible are offered make objective.

{0005}

[Means to Solve the Problems]

In addition to as for these inventors, when in order to achieve the aforementioned objective, result of diligent research, it uses compound which possesses specific anthracene structure which is displayed with the below-mentioned General Formula (1), as light-emitting material of organic EL device assembly of the intermolecular can be controlled by effect, as sterically hindered group of substituent X at the high light emitting brightness and efficiency, to low voltage converting drive voltage, Also element lifetime it is long, you discovered, this invention reached to completion.

{0006}


namely, this invention is something which offers light-emitting material for organic EL device which consists of anthracene derivative, said anthracene derivative which is displayed with below-mentioned General Formula (1).

{Chemical Formula 4 }

In Formula, X displays heteroaromatic group, substituted or unsubstituted carbon number 1 to 50 alkyl group, substituted or unsubstituted nucleus carbon number 6 to 50 aryloxy group, substituted or unsubstituted nucleus carbon number 6 to 50 aryl thio group, substituted or unsubstituted carbon number 1 to 50 alkoxy carbonyl group, or carboxyl group of cycloalkyl group, substituted or unsubstituted carbon number 1 to 50 alkoxy group, substituted or unsubstituted nucleus number of atoms 5~50 of halogen atom, hydroxyl group, nitro group, cyano group, substituted or unsubstituted carbon number 1 to 50 alkyl group, substituted or unsubstituted nucleus carbon number 6 to 50 aryl group, substituted or unsubstituted carbon number 5~50, inside at least one of X is heteroaromatic group, substituted or unsubstituted carbon number 1 to 50 alkyl group, substituted or unsubstituted nucleus carbon number 6 to 50 aryloxy group, substituted or unsubstituted nucleus carbon number 6 to 50 aryl thio group of cycloalkyl group, substituted or unsubstituted nucleus number of atoms 5~50 of substituted or unsubstituted nucleus carbon number 6 to 50

置換の核炭素数6~50のアリールチオ基である。

aryl group, substituted or unsubstituted carbon number 5~50.



Arは置換もしくは無置換の核炭素数10~50の縮合環アリール基であり、Ar'は置換もしくは無置換の核炭素数6~50のアリール基である。a及びbは、それぞれ0~4の整数であり、aとbが同時に0になることはない。また、Xが複数ある場合は、それぞれ同じでも異なってもよい。nは1~3の整数である。また、nが2以上の場合は、[]内の

【化5】

は、同じでも異なってもよい。


)

As for Ar with fused ring aryl group of substituted or unsubstituted nucleus carbon number 10~50, as for Ar' it is a substituted or unsubstituted nucleus carbon number 6 to 50 aryl group. As for a and b, respectively with integer 0 - 4, there are not times when a and b become simultaneously 0. In addition, when X is a plural, being same respectively, differing, it is possible to be. n is integer 1 - 3. In addition, when n is 2 or more, inside []

{Chemical Formula 5 }

Being same, differing, it is possible to be.

)



【0007】

また、本発明は、陰極と陽極間に少なくとも発光層を含む一層又は複数層からなる有機薄膜層が挟持されている有機EL素子において、該有機薄膜層の少なくとも1層が、前記有機EL素子用発光材料を単独もしくは混合物の成分として含有する有機EL素子を提供するものである。

【0008】

{0007}

In addition, as for this invention, at least 1 layer of said organic thin film layer, is something which offers organic EL device which contains light-emitting material for the aforementioned organic EL device as component of alone or mixture organic thin film layer which consists of one layer or multiple layers which at least includes light emitting layer between the cathode and anode in organic EL device which clamping is done.

{0008}

【発明の実施の形態】

本発明のアントラセン誘導体は、上記一般式(1)で表される化合物からなるものである。

一般式(1)において、ハロゲン原子、ヒドロキシル基、ニトロ基、シアノ基、置換もしくは無置換の炭素数1~50のアルキル基、置換もしくは無置換の核炭素数6~50のアリール基、置換もしくは無置換の炭素数5~50のシクロアルキル基、置換もしくは無置換の炭素数1~50のアルコキシ基、置換もしくは無置換の核原子数5~50の芳香族複素環基、置換もしくは無置換の炭素数1~50のアラルキル基、置換もしくは無置換の核炭素数6~50のアリールオキシ基、置換もしくは無置換の核炭素数6~50のアリールチオ基、置換もしくは無置換の炭素数1~50のアルコキシカルボニル基、又はカルボキシル基を表し、Xのうち少なくとも1つは、置換もしくは無置換の核炭素数6~50のアリール基、置換もしくは無置換の炭素数5~50のシクロアルキル基、置換もしくは無置換の核原子数5~50の芳香族複素環基、置換もしくは無置換の炭素数1~50のアラルキル基、置換もしくは無置換の核炭素数6~50のアリールオキシ基、置換もしくは無置換の核炭素数6~50のアリールチオ基である。

【0009】

一般式(1)において、a及びbは、それぞれ0~4の整数であり、 $a+b=1\sim 2$ であると好ましい。

aとbが同時に0になることはなく、Xが複数ある場合は、それぞれ同じでも異なってもよい。

【0010】

Xにおけるハロゲン原子の例としては、フッ素、塩素、臭素、ヨウ素が挙げられる。

Xにおける置換もしくは無置換のアルキル基の例としては、メチル基、エチル基、プロピル基、イソプロピル基、n-ブチル基、s-ブチル基、イソブチル基、t-ブチル基、n-ペンチル基、n-ヘキシル基、n-ヘプチル基、n-オクチル基、ヒドロキシメチル基、1-ヒドロキシエチル基、2-ヒドロキシエチル基、2-ヒドロキシイソブチル基、1,2-ジヒドロキシエチル基、1,3-ジヒドロキシイソプロピル基、2,3-ジヒドロキシー-ブチル基、1,2,3-トリヒドロキシプロピル基、クロロメチル基、1-クロロエチル基、2-クロロエチル基、2-クロロイソブチル基、1,2-ジクロロエチル基、1,3-ジクロロイソプロピル基、2,3-ジクロロ-ブチル基、1,2,3-トリク

[Embodiment of the Invention]

anthracene derivative of this invention is something which consists of compound which is displayed with above-mentioned General Formula (1).

In General Formula (1), heteroaromatic group, substituted or unsubstituted carbon number 1 to 50 aralkyl group, substituted or unsubstituted nucleus carbon number 6 to 50 aryloxy group, substituted or unsubstituted nucleus carbon number 6 to 50 aryl thio group, substituted or unsubstituted carbon number 1 to 50 alkoxy carbonyl group, or carboxyl group of cycloalkyl group, substituted or unsubstituted carbon number 1 to 50 alkoxy group, substituted or unsubstituted nucleus number of atoms 5~50 of halogen atom, hydroxyl group, nitro group, cyano group, substituted or unsubstituted carbon number 1 to 50 alkyl group, substituted or unsubstituted nucleus carbon number 6 to 50 aryl group, substituted or unsubstituted carbon number 5~50 is displayed, inside at least one of X is heteroaromatic group, substituted or unsubstituted carbon number 1 to 50 aralkyl group, substituted or unsubstituted nucleus carbon number 6 to 50 aryloxy group, substituted or unsubstituted nucleus carbon number 6 to 50 aryl thio group of cycloalkyl group, substituted or unsubstituted nucleus number of atoms 5~50 of substituted or unsubstituted nucleus carbon number 6 to 50 aryl group, substituted or unsubstituted carbon number 5~50.

{0009}

In General Formula (1), a and b, when with integer 0 - 4; it is $a + b = 1\sim 2$ respectively, is desirable.

When there are not times when a and b becomes simultaneously 0, X is a plural, being same respectively, differing, it is possible to be.

{0010}

You can list fluorine, chlorine, bromine, iodine as example of halogen atom in X.

As example of substituted or unsubstituted alkyl group in X, methyl group, ethyl group, propyl group, isopropyl group, n-butyl group, s-butyl group, isobutyl group, t-butyl group, n-pentyl group, n-hexyl group, n-heptyl group, n-octyl group, hydroxymethyl group, 1-hydroxyethyl group, 2-hydroxyethyl group, 2-hydroxyisobutyl group, 1,2-di hydroxyethyl group, 1,3-di hydroxyisopropyl group, 2,3-di hydroxy-t-butyl group, 1,2,3-tri hydroxy propyl basis and chloromethyl group, 1-chloroethyl group, 2-chloroethyl group, 2-chloroisobutyl group, 1,2-di chloroethyl group, 1,3-di clo Ro isopropyl group, 2,3-di clol#ro-x propyl basis and bromomethyl group, 1-bromoethyl group, 2-bromoethyl group, 2-bromo isobutyl group, 1,2-di ブロモ ethyl group, 1 and 3-di the ブロモ

ロロプロピル基、プロモメチル基、1-ブプロモエチル基、2-ブプロモエチル基、2-ブプロモイソブチル基、1, 2-ジブプロモエチル基、1, 3-ジブプロモイソブチル基、2, 3-ジブプロモ-*tert*-ブチル基、1, 2, 3-トリブプロモプロピル基、ヨードメチル基、1-ヨードエチル基、2-ヨードエチル基、2-ヨードイソブチル基、1, 2-ジヨードエチル基、1, 3-ジヨードイソブチル基、2, 3-ジヨード-*tert*-ブチル基、1, 2, 3-トリヨードプロピル基、アミノメチル基、1-アミノエチル基、2-アミノエチル基、2-アミノイソブチル基、1, 2-ジアミノエチル基、1, 3-ジアミノイソブチル基、2, 3-ジアミノ-*tert*-ブチル基、1, 2, 3-トリアミノプロピル基、シアノメチル基、1-シアノエチル基、2-シアノエチル基、2-シアノイソブチル基、1, 2-ジシアノエチル基、1, 3-ジシアノイソブチル基、2, 3-ジシアノ-*tert*-ブチル基、1, 2, 3-トリシアノプロピル基、ニトロメチル基、1-ニトロエチル基、2-ニトロエチル基、2-ニトロイソブチル基、1, 2-ジニトロエチル基、1, 3-ジニトロイソブチル基、2, 3-ジニトロ-*tert*-ブチル基、1, 2, 3-トリニトロプロピル基等が挙げられる。

【0011】

Xにおける置換もしくは無置換のアリール基の例としては、フェニル基、1-ナフチル基、2-ナフチル基、1-アントリル基、2-アントリル基、9-アントリル基、1-フェナントリル基、2-フェナントリル基、3-フェナントリル基、4-フェナントリル基、9-フェナントリル基、1-ナフタセニル基、2-ナフタセニル基、9-ナフタセニル基、1-ピレニル基、2-ピレニル基、4-ピレニル基、2-ビフェニルイル基、3-ビフェニルイル基、4-ビフェニルイル基、*p*-ターフェニル-4-イル基、*p*-ターフェニル-3-イル基、*p*-ターフェニル-2-イル基、*m*-ターフェニル-4-イル基、*m*-ターフェニル-3-イル基、*m*-ターフェニル-2-イル基、*o*-トリル基、*m*-トリル基、*p*-*tert*-ブチルフェニル基、*p*-(2-フェニルプロピル)フェニル基、3-メチル-2-ナフチル基、4-メチル-1-ナフチル基、4-メチル-1-アントリル基、4'-メチルビフェニルイル基、4'-*tert*-ブチル-*p*-ターフェニル-4-イル基等が挙げられる。

Xにおける置換もしくは無置換のシクロアルキル基の例としては、シクロプロピル基、シクロブチル基、シクロペンチル基、シクロヘキシル基、4-メチルシクロヘキシル、アダマンチル基、ノルボルニル基等が挙げられる。

【0012】

isopropyl group, 2,3-di isobutoxy amino isopropyl group, 2,3-di amino -*t*-butyl group, 1,2,3-triamino propyl basis, You can list cyanomethyl group, 1-cyanoethyl group, 2-cyanoethyl group, 2-cyano isobutyl group, 1,2-di cyanoethyl group, 1,3-di cyano isopropyl group, 2,3-di cyano -*t*-butyl group, 1,2,3-tri cyanopropyl group, nitro methyl group, 1-nitro ethyl group, 2-nitro ethyl group, 2-nitro isobutyl group, 1,2-di nitro ethyl group, 1,3-di nitro isopropyl group, 2,3-di nitro -*t*-butyl group, 1,2,3-tri nitro propyl group etc. *t*-butyl group, 1,2,3-trichloro-*t*-butyl group, 1,2,3-tribromo propyl group, iodoethyl group, 1-iodoethyl group, 2-iodoethyl group, 2-iodo isobutyl group, 1,2-di iodoethyl group, 1,3-di iodo isopropyl group, 2,3-di iodo -*t*-butyl group, 1,2,3-tri iodo propyl group, aminomethyl group, 1-aminoethyl group, 2-aminoethyl group, 2-amino isobutyl group, 1,2-di aminoethyl group, 1,3-di

{0011}

You can list phenyl group, 1-naphthyl group, 2-naphthyl group, 1-anthryl group, 2-anthryl group, 9-anthryl group, 1-phenanthryl group, 2-phenanthryl group, 3-phenanthryl group, 4-phenanthryl group, 9-phenanthryl group, 1-naphacenyl group, 2-naphacenyl group, 9-naphacenyl group, 1-pyrenyl group, 2-pyrenyl group, 4-pyrenyl group, 2-biphenyl yl group, 3-biphenyl yl group, 4-biphenyl yl group, *p*-terphenyl -4-yl group, *p*-terphenyl -3-yl group, *p*-terphenyl -2-yl group, *m*-terphenyl -4-yl group, *m*-terphenyl -3-yl group, *m*-terphenyl -2-yl group, *o*-tolyl group, *m*-tolyl group, *p*-tolyl group, *p*-*t*-butyl phenyl group, *p*-(2-phenyl propyl) phenyl group, 3-methyl-2-naphthyl group, 4-methyl-1-naphthyl group, 4-methyl-1-anthryl group, 4'-methylbiphenyl yl group, 4'-*tert*-butyl -*p*-terphenyl -4-yl group etc as example of substituted or unsubstituted aryl group in the X.

You can list cyclopropyl group, cyclobutyl group, cyclopentyl group, cyclohexyl group, 4-methyl cyclohexyl, adamantyl group, norbornyl group etc as example of substituted or unsubstituted cycloalkyl group in X.

{0012}

Xにおける置換もしくは無置換のアルコキシ基は、-OYで表される基であり、Yの例としては、メチル基、エチル基、プロピル基、イソプロピル基、n-ブチル基、s-ブチル基、イソブチル基、t-ブチル基、n-ペンチル基、n-ヘキシル基、n-ヘプチル基、n-オクチル基、ヒドロキシメチル基、1-ヒドロキシエチル基、2-ヒドロキシエチル基、2-ヒドロキシイソブチル基、1, 2-ジヒドロキシエチル基、1, 3-ジヒドロキシイソプロピル基、2, 3-ジヒドロキシ-tert-ブチル基、1, 2, 3-トリヒドロキシプロピル基、クロロメチル基、1-クロロエチル基、2-クロロエチル基、2-クロロイソブチル基、1, 2-ジクロロエチル基、1, 3-ジクロロイソプロピル基、2, 3-ジクロロ-tert-ブチル基、1, 2, 3-トリクロロプロピル基、ブromoメチル基、1-ブromoエチル基、2-ブromoエチル基、2-ブromoイソブチル基、1, 2-ジブromoエチル基、1, 3-ジブromoイソプロピル基、2, 3-ジブromo-tert-ブチル基、1, 2, 3-トリブromoプロピル基、ヨードメチル基、1-ヨードエチル基、2-ヨードエチル基、2-ヨードイソブチル基、1, 2-ジヨードエチル基、1, 3-ジヨードイソプロピル基、2, 3-ジヨード-tert-ブチル基、1, 2, 3-トリヨードプロピル基、アミノメチル基、1-アミノエチル基、2-アミノエチル基、2-アミノイソブチル基、1, 2-ジアミノエチル基、1, 3-ジアミノイソプロピル基、2, 3-ジアミノ-tert-ブチル基、1, 2, 3-トリアミノプロピル基、シアノメチル基、1-シアノエチル基、2-シアノエチル基、2-シアノイソブチル基、1, 2-ジシアノエチル基、1, 3-ジシアノイソプロピル基、2, 3-ジシアノ-tert-ブチル基、1, 2, 3-トリシアノプロピル基、ニトロメチル基、1-ニトロエチル基、2-ニトロエチル基、2-ニトロイソブチル基、1, 2-ジニトロエチル基、1, 3-ジニトロイソプロピル基、2, 3-ジニトロ-tert-ブチル基、1, 2, 3-トリニトロプロピル基等が挙げられる。

{0013}

Xにおける置換もしくは無置換の芳香族複素環基の例としては、1-ピロリル基、2-ピロリル基、3-ピロリル基、ピラジニル基、2-ピリジニル基、3-ピリジニル基、4-ピリジニル基、1-インドリル基、2-インドリル基、3-インドリル基、4-インドリル基、5-インドリル基、6-インドリル基、7-インドリル基、1-イソインドリル基、2-イソインドリル基、3-イソインドリル基、4-イソインドリル基、5-イソインドリル基、6-イソインドリル基、7-イソインドリル基、2-フリル基、3-フリル基、2-ベンゾフラニル基、3-ベンゾフラニル基、4-ベンゾフラニル基、5-ベンゾフラニル基、6-ベンゾフラニル基、7-

As for substituted or unsubstituted alkoxy group in X, with group which is displayed with -OY, as example of Y, methyl group, ethyl group, propyl group, isopropyl group, n-butyl group, s-butyl group, isobutyl group, t-butyl group, n-pentyl group, n-hexyl group, n-heptyl group, n-octyl group, hydroxymethyl group, 1-hydroxyethyl group, 2-hydroxyethyl group, 2-hydroxy isobutyl group, 1,2-di hydroxyethyl group, 1,3-di hydroxy isopropyl group, 2,3-di hydroxy-t-butyl group, 1,2,3-trihydroxy propyl basis and chloromethyl group, 1-chloro ethyl group, 2-chloroethyl group, 2-chloro isobutyl group, 1,2-di chloroethyl group, 1,3-di clo Ro isopropyl group, 2,3-di clol#ro-x propyl basis and bromomethyl group, 1-bromoethyl group, 2-bromoethyl group, 2-bromo isobutyl group, 1,2-di ブロモethyl group, 1 and 3-di ブロモ isopropyl group, 2,3-di l#buromo-x amino isopropyl group, 2,3-di amino -t-butyl group, 1,2,3-triamino you can list propyl basis and cyanomethyl group, 1-cyanoethyl group, 2-cyanoethyl group, 2-cyano isobutyl group, 1,2-di cyanoethyl group, 1,3-di cyano isopropyl group, 2,3-di cyano -t-butyl group, 1,2,3-tri cyanopropyl group, nitro methyl group, 1-nitro ethyl group, 2-nitro ethyl group, 2-nitro isobutyl group, 1,2-di nitro ethyl group, 1,3-di nitro isopropyl group, 2,3-di nitro -t-butyl group, 1,2,3-tri nitro propyl group etc. t-butyl group, 1,2,3-trichlorot-butyl group, 1,2,3-tribromo propyl group, iodomethyl group, 1-iodoethyl group, 2-iodoethyl group, 2-iodo isobutyl group, 1,2-di iodoethyl group, 1,3-di iodo isopropyl group, 2,3-di iodo -t-butyl group, 1,2,3-tri iodo propyl group, aminomethyl group, 1-aminoethyl group, 2-aminoethyl group, 2-amino isobutyl group, 1,2-di aminoethyl group, 1,3-di

{0013}

As example of substituted or unsubstituted heteroaromatic group in X, 1-pyrrolyl group, 2-pyrrolyl group, 3-pyrrolyl group, pyridazinyl group, 2-pyridinyl group, 3-pyridinyl group, 4-pyridinyl group, 1-indolyl group, 2-indolyl group, 3-indolyl group, 4-indolyl group, 5-indolyl group, 6-indolyl group, 7-indolyl group, 1-iso indolyl group, 2-iso indolyl group, 3-iso indolyl group, 4-iso indolyl group, 5-iso indolyl group, 6-iso indolyl group, 7-iso indolyl group, 2-furyl group, 3-furyl group, 2-benzofuranyl group, 3-benzofuranyl group, 4-benzofuranyl group, 5-benzofuranyl group, 6-benzofuranyl group, 7-benzofuranyl group, 1-isobenzofuranyl group, 3-isobenzofuranyl group, 4-isobenzofuranyl group, 5-

ベンゾフラニル基、1-イソベンゾフラニル基、3-イソベンゾフラニル基、4-イソベンゾフラニル基、5-イソベンゾフラニル基、6-イソベンゾフラニル基、7-イソベンゾフラニル基、キノリル基、3-キノリル基、4-キノリル基、5-キノリル基、6-キノリル基、7-キノリル基、8-キノリル基、1-イソキノリル基、3-イソキノリル基、4-イソキノリル基、5-イソキノリル基、6-イソキノリル基、7-イソキノリル基、8-イソキノリル基、2-キノキサリル基、5-キノキサリル基、6-キノキサリル基、1-カルバゾリル基、2-カルバゾリル基、3-カルバゾリル基、4-カルバゾリル基、9-カルバゾリル基、1-フェナンスリジニル基、2-フェナンスリジニル基、3-フェナンスリジニル基、4-フェナンスリジニル基、6-フェナンスリジニル基、7-フェナンスリジニル基、8-フェナンスリジニル基、9-フェナンスリジニル基、10-フェナンスリジニル基、1-アクリジニル基、2-アクリジニル基、3-アクリジニル基、4-アクリジニル基、9-アクリジニル基、1, 7-フェナンスロリン-2-イル基、1, 7-フェナンスロリン-3-イル基、1, 7-フェナンスロリン-4-イル基、1, 7-フェナンスロリン-5-イル基、1, 7-フェナンスロリン-6-イル基、1, 7-フェナンスロリン-8-イル基、1, 7-フェナンスロリン-9-イル基、1, 7-フェナンスロリン-10-イル基、1, 8-フェナンスロリン-2-イル基、1, 8-フェナンスロリン-3-イル基、1, 8-フェナンスロリン-4-イル基、1, 8-フェナンスロリン-5-イル基、1, 8-フェナンスロリン-6-イル基、1, 8-フェナンスロリン-7-イル基、1, 8-フェナンスロリン-9-イル基、1, 8-フェナンスロリン-10-イル基、1, 9-フェナンスロリン-2-イル基、1, 9-フェナンスロリン-3-イル基、1, 9-フェナンスロリン-4-イル基、1, 9-フェナンスロリン-5-イル基、1, 9-フェナンスロリン-6-イル基、1, 9-フェナンスロリン-7-イル基、1, 9-フェナンスロリン-8-イル基、1, 9-フェナンスロリン-10-イル基、1, 10-フェナンスロリン-2-イル基、1, 10-フェナンスロリン-3-イル基、1, 10-フェナンスロリン-4-イル基、1, 10-フェナンスロリン-5-イル基、2, 9-フェナンスロリン-1-イル基、2, 9-フェナンスロリン-3-イル基、2, 9-フェナンスロリン-4-イル基、2, 9-フェナンスロリン-5-イル基、2, 9-フェナンスロリン-6-イル基、2, 9-フェナンスロリン-7-イル基、2, 9-フェナンスロリン-8-イル基、2, 9-フェナンスロリン-10-イル基、2, 8-フェナンスロリン-1-イル基、2, 8-フェナンスロリン-3-イル基、2, 8-フェナンスロリン-4-イル基、2, 8-フェナ

isobenzofuranyl group, 6 - isobenzofuranyl group, 7 - isobenzofuranyl group, quinolyl group, 3 - quinolyl group, 4 - quinolyl group, 5 - quinolyl group, 6 - quinolyl group, 7 - quinolyl group, 8 - quinolyl group, 1 - isoquinolyl group, 3 - isoquinolyl group, 4 - isoquinolyl group, 5 - isoquinolyl group, 6 - isoquinolyl group, 7 - isoquinolyl group, 8 - isoquinolyl group, 2 - quinoxaliny basis, 5 - quinoxaliny basis, 6 - quinoxaliny basis, 1 - carbozoyl group, 2 - carbozoyl group, 3 - carbozoyl group, 4 - carbozoyl group, 9 - carbozoyl group, 1 - phenanthridiny basis, 2 - phenanthridiny basis, 3 - phenanthridiny basis, 4 - phenanthridiny basis, 6 - phenanthridiny basis, 7 - phenanthridiny basis, 8 - phenanthridiny basis, 9 - phenanthridiny basis, 10 - phenanthridiny basis, 1 - acridiny group, 2 - acridiny group, 3 - acridiny group, 4 - acridiny group, 9 - acridiny group, 1,7 - phenanthroline - 2 -yl group, 1,7 - phenanthroline - 3 -yl group, 1,7 - phenanthroline - 4 -yl group, 1,7 - phenanthroline - 5 -yl group, 1,7 - phenanthroline - 6 -yl group, 1,7 - phenanthroline - 8 -yl group, 1,7 - phenanthroline - 9 -yl group, 1,7 - phenanthroline - 10 -yl group, 1,8 - phenanthroline - 2 -yl group, 1,8 - phenanthroline - 3 -yl group, 1,8 - phenanthroline - 4 -yl group, 1,8 - phenanthroline - 5 -yl group, 1,8 - phenanthroline - 6 -yl group, 1,8 - phenanthroline - 7 -yl group, 1,8 - phenanthroline - 9 -yl group, 1,8 - phenanthroline - 10 -yl group, 1,9 - phenanthroline - 2 -yl group, 1,9 - phenanthroline - 3 -yl group, 1,9 - phenanthroline - 4 -yl group, 1,9 - phenanthroline - 5 -yl group, 1,9 - phenanthroline - 6 -yl group, 1,9 - phenanthroline - 7 -yl group, 1,9 - phenanthroline - 8 -yl group, 1,9 - phenanthroline - 10 -yl group, 1,10 - phenanthroline - 2 -yl group, 1,10 - phenanthroline - 3 -yl group, 1,10 - phenanthroline - 4 -yl group, 1,10 - phenanthroline - 5 -yl group, 2,9 - phenanthroline - 1 -yl group, 2,9 - phenanthroline - 3 -yl group, 2,9 - phenanthroline - 4 -yl group, 2,9 - phenanthroline - 5 -yl group, 2,9 - phenanthroline - 6 -yl group, 2,9 - phenanthroline - 7 -yl group, 2,9 - phenanthroline - 8 -yl group, 2,9 - phenanthroline - 10 -yl group, 2,8 - phenanthroline - 1 -yl group, 2,8 - phenanthroline - 3 -yl group, 2,8 - phenanthroline - 4 -yl group, 2,8 - phenanthroline - 5 -yl group, 2,8 - phenanthroline - 6 -yl group, 2,8 - phenanthroline - 7 -yl group, 2,8 - phenanthroline - 9 -yl group, 2,8 - phenanthroline - 10 -yl group, 2,7 - phenanthroline - 1 -yl group, 2,7 - phenanthroline - 3 -yl group, 2,7 - phenanthroline - 4 -yl group, 2,7 - phenanthroline - 5 -yl group, 2,7 - phenanthroline - 6 -yl group, 2,7 - phenanthroline - 8 -yl group, 2,7 - phenanthroline - 9 -yl group, 2,7 - phenanthroline - 10 -yl group, 1 - phenaziny basis, 2 - phenaziny basis, 1 - phenothiaziny basis, 2 - phenothiaziny basis, 3 - phenothiaziny basis, 4 - phenothiaziny basis, 10

ンスロリン-5-イル基、2, 8-フェナンスロリン-6-イル基、2, 8-フェナンスロリン-7-イル基、2, 8-フェナンスロリン-9-イル基、2, 8-フェナンスロリン-10-イル基、2, 7-フェナンスロリン-1-イル基、2, 7-フェナンスロリン-3-イル基、2, 7-フェナンスロリン-4-イル基、2, 7-フェナンスロリン-5-イル基、2, 7-フェナンスロリン-6-イル基、2, 7-フェナンスロリン-8-イル基、2, 7-フェナンスロリン-9-イル基、2, 7-フェナンスロリン-10-イル基、1-フェナジニル基、2-フェナジニル基、1-フェノチアジニル基、2-フェノチアジニル基、3-フェノチアジニル基、4-フェノチアジニル基、10-フェノチアジニル基、1-フェノキサジニル基、2-フェノキサジニル基、3-フェノキサジニル基、4-フェノキサジニル基、10-フェノキサジニル基、2-オキサゾリル基、4-オキサゾリル基、5-オキサゾリル基、2-オキサジアゾリル基、5-オキサジアゾリル基、3-フラザニル基、2-チエニル基、3-チエニル基、2-メチルピロール-1-イル基、2-メチルピロール-3-イル基、2-メチルピロール-4-イル基、2-メチルピロール-5-イル基、3-メチルピロール-1-イル基、3-メチルピロール-2-イル基、3-メチルピロール-4-イル基、3-メチルピロール-5-イル基、2-*t*-ブチルピロール-4-イル基、3-(2-フェニルプロピル)ピロール-1-イル基、2-メチル-1-インドリル基、4-メチル-1-インドリル基、2-メチル-3-インドリル基、4-メチル-3-インドリル基、2-*t*-ブチル-1-インドリル基、4-*t*-ブチル-1-インドリル基、2-*t*-ブチル-3-インドリル基、4-*t*-ブチル-3-インドリル基等が挙げられる。

【0014】

Xにおける置換もしくは無置換のアラルキル基の例としては、ベンジル基、1-フェニルエチル基、2-フェニルエチル基、1-フェニルイソプロピル基、2-フェニルイソプロピル基、フェニル-*t*-ブチル基、 α -ナフチルメチル基、1- α -ナフチルエチル基、2- α -ナフチルエチル基、1- α -ナフチルイソプロピル基、2- α -ナフチルイソプロピル基、 β -ナフチルメチル基、1- β -ナフチルエチル基、2- β -ナフチルエチル基、1- β -ナフチルイソプロピル基、2- β -ナフチルイソプロピル基、1-ピロリルメチル基、2-(1-ピロリル)エチル基、*p*-メチルベンジル基、*m*-メチルベンジル基、*o*-メチルベンジル基、*p*-クロロベンジル基、*m*-クロロベンジル基、*o*-クロロベンジル基、*p*-ブロモベンジル基、*m*-ブロモベンジル基、*o*-ブロモベンジル基、*p*-ヨードベンジル基、*m*-ヨード

-phenothiazinyl basis, 1-phenoxazinyl basis, 2-phenoxazinyl basis, 3-phenoxazinyl basis, 4-phenoxazinyl basis, 10-phenoxazinyl basis, 2-oxazolyl group, 4-oxazolyl group, 5-oxazolyl group, 2-oxadiazolyl group, 5-oxadiazolyl group, 3-furazanyl group, 2-thienyl group, 3-thienyl group, 2-methyl pyrrole-1-yl group, 2-methyl pyrrole-3-yl group, 2-methyl pyrrole-4-yl group, 2-methyl pyrrole-5-yl group, 3-methyl pyrrole-1-yl group, 3-methyl pyrrole-2-yl group, 3-methyl pyrrole-4-yl group, 3-methyl pyrrole-

{0014}

benzyl group, 1-phenylethyl group, 2-phenylethyl group, 1-phenyl isopropyl group, 2-phenyl isopropyl group, phenyl-*t*-butyl group, *al*-naphthyl methyl group, 1-the;*al*-naphthyl ethyl group, 2-the;*al*-naphthyl ethyl group, 1-the;*al*-naphthyl isopropyl group, 2-the;*al*-naphthyl isopropyl group, the;*be*-naphthyl methyl group, 1-the;*be*-naphthyl ethyl group, 2-the;*be*-naphthyl ethyl group, 1-the;*be*-naphthyl isopropyl group, 2-the;*be*-naphthyl isopropyl group, 1-pyrrolyl methyl group, 2-you can list (1-pyrrolyl) ethyl group, *p*-methylbenzyl group, *m*-methylbenzyl group, *o*-methylbenzyl group, *p*-chloro benzyl group, *m*-chloro benzyl group, *o*-chloro benzyl group, *p*-bromo benzyl group, *m*-bromo benzyl group, *o*-bromo benzyl group, *p*-iodo benzyl group, *m*-iodo benzyl group, *o*-iodo benzyl group, *p*-hydroxy benzyl group, *m*-hydroxy benzyl group, *o*-hydroxy benzyl group, *p*-amino benzyl group, *m*-amino benzyl group, *o*-amino benzyl

ベンジル基、*o*-ヨードベンジル基、*p*-ヒドロキシベンジル基、*m*-ヒドロキシベンジル基、*o*-ヒドロキシベンジル基、*p*-アミノベンジル基、*m*-アミノベンジル基、*o*-アミノベンジル基、*p*-ニトロベンジル基、*m*-ニトロベンジル基、*o*-ニトロベンジル基、*p*-シアノベンジル基、*m*-シアノベンジル基、*o*-シアノベンジル基、1-ヒドロキシ-2-フェニルイソプロピル基、1-クロロ-2-フェニルイソプロピル基、トリチル基等が挙げられる。

【0015】

Xにおける置換もしくは無置換のアリールオキシ基は、-OZと表され、Zの例としてはフェニル基、1-ナフチル基、2-ナフチル基、1-アントリル基、2-アントリル基、9-アントリル基、1-フェナントリル基、2-フェナントリル基、3-フェナントリル基、4-フェナントリル基、9-フェナントリル基、1-ナフタセニル基、2-ナフタセニル基、9-ナフタセニル基、1-ピレニル基、2-ピレニル基、4-ピレニル基、2-ビフェニル基、3-ビフェニル基、4-ビフェニル基、*p*-ターフェニル-4-イル基、*p*-ターフェニル-3-イル基、*p*-ターフェニル-2-イル基、*m*-ターフェニル-4-イル基、*m*-ターフェニル-3-イル基、*m*-ターフェニル-2-イル基、*o*-トリル基、*m*-トリル基、*p*-トリル基、*p*-*t*-ブチルフェニル基、*p*-(2-フェニルプロピル)フェニル基、3-メチル-2-ナフチル基、4-メチル-1-ナフチル基、4-メチル-1-アントリル基、4'-メチルビフェニル基、4"-*t*-ブチル-*p*-ターフェニル-4-イル基、2-ピロリル基、3-ピロリル基、ピラジニル基、2-ピリジニル基、3-ピリジニル基、4-ピリジニル基、2-インドリル基、3-インドリル基、4-インドリル基、5-インドリル基、6-インドリル基、7-インドリル基、1-イソインドリル基、3-イソインドリル基、4-イソインドリル基、5-イソインドリル基、6-イソインドリル基、7-イソインドリル基、2-フリル基、3-フリル基、2-ベンゾフラニル基、3-ベンゾフラニル基、4-ベンゾフラニル基、5-ベンゾフラニル基、6-ベンゾフラニル基、7-ベンゾフラニル基、1-イソベンゾフラニル基、3-イソベンゾフラニル基、4-イソベンゾフラニル基、5-イソベンゾフラニル基、6-イソベンゾフラニル基、7-イソベンゾフラニル基、2-キノリル基、3-キノリル基、4-キノリル基、5-キノリル基、6-キノリル基、7-キノリル基、8-キノリル基、1-イソキノリル基、3-イソキノリル基、4-イソキノリル基、5-イソキノリル基、6-イソキノリル基、7-イソキノリル基、8-イソキノリル基、2-キノキサリニル基、5-キノキサリニル基、6-キノキサリニル

group, *p*-nitrobenzyl group, *m*-nitrobenzyl group, *o*-nitrobenzyl group, *p*-cyano benzyl group, *m*-cyano benzyl group, *o*-cyano benzyl group, 1-hydroxy-2-phenyl isopropyl group, 1-chloro-2-phenyl isopropyl group, trityl group etc as example of substituted or unsubstituted aralkyl group in the X.

{0015}

As for substituted or unsubstituted aryloxy group in X, as example of -OZ and displaying and Z phenyl group, 1-naphthyl group, 2-naphthyl group, 1-anthryl group, 2-anthryl group, 9-anthryl group, 1-phenanthryl group, 2-phenanthryl group, 3-phenanthryl group, 4-phenanthryl group, 9-phenanthryl group, 1-naphacenyl group, 2-naphacenyl group, 9-naphacenyl group, 1-pyrenyl group, 2-pyrenyl group, 4-pyrenyl group, 2-biphenyl yl group, 3-biphenyl yl group, 4-biphenyl yl group, *p*-terphenyl-4-yl group, *p*-terphenyl-3-yl group, *p*-terphenyl-2-yl group, *m*-terphenyl-4-yl group, *m*-terphenyl-3-yl group, *m*-terphenyl-2-yl group, *o*-tolyl group, *m*-tolyl group, *p*-tolyl group, *p*-*t*-butyl phenyl group, *p*-(2-phenyl propyl) phenyl group, 3-methyl-2-naphthyl group, 4-methyl-1-naphthyl group, 4-methyl-1-anthryl group, 4'-methylbiphenyl group, 4"-*t*-butyl-*p*-terphenyl-4-yl group, 2-pyrrolyl group, 3-pyrrolyl group, pyridazinyl group, 2-pyridinyl group, 3-pyridinyl group, 4-pyridinyl group, 2-indolyl group, 3-indolyl group, 4-indolyl group, 5-indolyl group, 6-indolyl group, 7-indolyl group, 1-isoindolyl group, 3-isoindolyl group, 4-isoindolyl group, 5-isoindolyl group, 6-isoindolyl group, 7-isoindolyl group, 2-furyl group, 3-furyl group, 2-benzofuranyl group, 3-benzofuranyl group, 4-benzofuranyl group, 5-benzofuranyl group, 6-benzofuranyl group, 7-benzofuranyl group, 1-isobenzofuranyl group, 3-isobenzofuranyl group, 4-isobenzofuranyl group, 5-isobenzofuranyl group, 6-isobenzofuranyl group, 7-isobenzofuranyl group, 2-quinolyl group, 3-quinolyl group, 4-quinolyl group, 5-quinolyl group, 6-quinolyl group, 7-quinolyl group, 8-quinolyl group, 1-isoquinolyl group, 3-isoquinolyl group, 4-isoquinolyl group, 5-isoquinolyl group, 6-isoquinolyl group, 7-isoquinolyl group, 8-isoquinolyl group, 2-quinoxaliny basis, 5-quinoxaliny basis, 6-quinoxaliny basis, 1-carbozoly group, 2-carbozoly group, 3-carbozoly group, 4-carbozoly group, 1-phenanthridinyl basis, 2-phenanthridinyl basis, 3-phenanthridinyl basis, 4-phenanthridinyl basis, 6-phenanthridinyl basis, 7-phenanthridinyl basis, 8-phenanthridinyl basis, 9-phenanthridinyl basis, 10

基、1-カルバゾリル基、2-カルバゾリル基、3-カルバゾリル基、4-カルバゾリル基、1-フェナンスリジニル基、2-フェナンスリジニル基、3-フェナンスリジニル基、4-フェナンスリジニル基、6-フェナンスリジニル基、7-フェナンスリジニル基、8-フェナンスリジニル基、9-フェナンスリジニル基、10-フェナンスリジニル基、1-アクリジニル基、2-アクリジニル基、3-アクリジニル基、4-アクリジニル基、9-アクリジニル基、1, 7-フェナンスロリン-2-イル基、1, 7-フェナンスロリン-3-イル基、1, 7-フェナンスロリン-4-イル基、1, 7-フェナンスロリン-5-イル基、1, 7-フェナンスロリン-6-イル基、1, 7-フェナンスロリン-8-イル基、1, 7-フェナンスロリン-10-イル基、1, 8-フェナンスロリン-2-イル基、1, 8-フェナンスロリン-3-イル基、1, 8-フェナンスロリン-4-イル基、1, 8-フェナンスロリン-5-イル基、1, 8-フェナンスロリン-6-イル基、1, 8-フェナンスロリン-7-イル基、1, 8-フェナンスロリン-9-イル基、1, 8-フェナンスロリン-10-イル基、1, 9-フェナンスロリン-2-イル基、1, 9-フェナンスロリン-3-イル基、1, 9-フェナンスロリン-4-イル基、1, 9-フェナンスロリン-5-イル基、1, 9-フェナンスロリン-6-イル基、1, 9-フェナンスロリン-7-イル基、1, 9-フェナンスロリン-8-イル基、1, 9-フェナンスロリン-10-イル基、1, 10-フェナンスロリン-2-イル基、1, 10-フェナンスロリン-3-イル基、1, 10-フェナンスロリン-4-イル基、1, 10-フェナンスロリン-5-イル基、2, 9-フェナンスロリン-1-イル基、2, 9-フェナンスロリン-3-イル基、2, 9-フェナンスロリン-4-イル基、2, 9-フェナンスロリン-5-イル基、2, 9-フェナンスロリン-6-イル基、2, 9-フェナンスロリン-7-イル基、2, 9-フェナンスロリン-8-イル基、2, 9-フェナンスロリン-10-イル基、2, 8-フェナンスロリン-1-イル基、2, 8-フェナンスロリン-3-イル基、2, 8-フェナンスロリン-4-イル基、2, 8-フェナンスロリン-5-イル基、2, 8-フェナンスロリン-6-イル基、2, 8-フェナンスロリン-7-イル基、2, 8-フェナンスロリン-9-イル基、2, 8-フェナンスロリン-10-イル基、2, 7-フェナンスロリン-1-イル基、2, 7-フェナンスロリン-3-イル基、2, 7-フェナンスロリン-4-イル基、2, 7-フェナンスロリン-5-イル基、2, 7-フェナンスロリン-6-イル基、2, 7-フェナンスロリン-8-イル基、2, 7-フェナンスロリン-9-イル基、2, 7-フェナンスロリン-10-イル基、1-フェナジニル基、2-フェナジニ

-phenanthridinyl basis, 1-acridinyl group, 2-acridinyl group, 3-acridinyl group, 4-acridinyl group, 9-acridinyl group, 1,7-phenanthroline-2-yl group, 1,7-phenanthroline-3-yl group, 1,7-phenanthroline-4-yl group, 1,7-phenanthroline-5-yl group, 1,7-phenanthroline-6-yl group, 1,7-phenanthroline-8-yl group, 1,7-phenanthroline-9-yl group, 1,7-phenanthroline-10-yl group, 1,8-phenanthroline-2-yl group, 1,8-phenanthroline-3-yl group, 1,8-phenanthroline-4-yl group, 1,8-phenanthroline-5-yl group, 1,8-phenanthroline-6-yl group, 1,8-phenanthroline-7-yl group, 1,8-phenanthroline-9-yl group, 1,8-phenanthroline-10-yl group, 1,9-phenanthroline-2-yl group, 1,9-phenanthroline-3-yl group, 1,9-phenanthroline-4-yl group, 1,9-phenanthroline-5-yl group, 1,9-phenanthroline-6-yl group, 1,9-phenanthroline-7-yl group, 1,9-phenanthroline-8-yl group, 1,9-phenanthroline-10-yl group, 1,10-phenanthroline-2-yl group, 1,10-phenanthroline-3-yl group, 1,10-phenanthroline-4-yl group, 1,10-phenanthroline-5-yl group, 2,9-phenanthroline-1-yl group, 2,9-phenanthroline-3-yl group, 2,9-phenanthroline-4-yl group, 2,9-phenanthroline-5-yl group, 2,9-phenanthroline-6-yl group, 2,9-phenanthroline-7-yl group, 2,9-phenanthroline-8-yl group, 2,9-phenanthroline-10-yl group, 2,8-phenanthroline-1-yl group, 2,8-phenanthroline-3-yl group, 2,8-phenanthroline-4-yl group, 2,8-phenanthroline-5-yl group, 2,8-phenanthroline-6-yl group, 2,8-phenanthroline-7-yl group, 2,8-phenanthroline-9-yl group, 2,8-phenanthroline-10-yl group, 2,7-phenanthroline-1-yl group, 2,7-phenanthroline-3-yl group, 2,7-phenanthroline-4-yl group, 2,7-

ル基、1-フェノチアジニル基、2-フェノチアジニル基、3-フェノチアジニル基、4-フェノチアジニル基、1-フェノキサジニル基、2-フェノキサジニル基、3-フェノキサジニル基、4-フェノキサジニル基、2-オキサゾリル基、4-オキサゾリル基、5-オキサゾリル基、2-オキサジアゾリル基、5-オキサジアゾリル基、3-フラザニル基、2-チエニル基、3-チエニル基、2-メチルピロール-1-イル基、2-メチルピロール-3-イル基、2-メチルピロール-4-イル基、2-メチルピロール-5-イル基、3-メチルピロール-1-イル基、3-メチルピロール-2-イル基、3-メチルピロール-4-イル基、3-メチルピロール-5-イル基、2-*t*-ブチルピロール-4-イル基、3-(2-フェニルプロピル)ピロール-1-イル基、2-メチル-1-インドリル基、4-メチル-1-インドリル基、2-メチル-3-インドリル基、4-メチル-3-インドリル基、2-*t*-ブチル-1-インドリル基、4-*t*-ブチル-1-インドリル基、2-*t*-ブチル-3-インドリル基、4-*t*-ブチル-3-インドリル基等が挙げられる。

【0016】

Xにおける置換もしくは無置換のアリールチオ基は、-SZと表され、Zの例としては前記アリールオキシ基のZと同様のものが挙げられる。

Xにおける置換もしくは無置換のアルコキシカルボニル基は-COOYと表され、Yの例としては、前記アルコキシ基におけるYと同様のものが挙げられる。

【0017】

一般式(1)において、Arは置換もしくは無置換の核炭素数10~50の縮合環アリール基であり、Ar'は置換もしくは無置換の核炭素数6~50のアリール基である。

Arの縮合環アリール基の例としては、下記の一般式

【化6】

(Ar(1))は、置換もしくは無置換の核炭素数6~50のアリール基である。

{0016}

As for substituted or unsubstituted aryl thio group in X, you can list those which are similar to Z of aforementioned aryloxy group as example of -SZ and the displaying and Z.

As for substituted or unsubstituted alkoxy carbonyl group in X you can list those which are similar to Y in aforementioned alkoxy group as example of -COOY and the displaying and Y.


{0017}

In General Formula (1), as for Ar with fused ring aryl group of substituted or unsubstituted nucleus carbon number 10~50, as for Ar' it is a substituted or unsubstituted nucleus carbon number 6 to 50 aryl group.

As example of fused ring aryl group of Ar, below-mentioned General Formula

{Chemical Formula 6}

(Ar (1) is substituted or unsubstituted nucleus carbon number 6 to 50 aryl group.)



から選べれる基が挙げられ、アルコキシ基、アルキル基、フェニル基、アルキルフェニル基で置換されていてもよい。

Ar(1)のアリール基としては、前述したXにおけるアリール基と同様のものが挙げられる。

一般式(1)において、Ar'のアリール基の具体例としては、前述したXにおけるアリール基と同様のものが挙げられる。

【0018】

nは1～3の整数である。

また、nが2以上の場合は、[]内の

【化7】

は、同じでも異なってもよい。

Empty choose れる be able to list basis, with alkoxy group, alkyl group, phenyl group, alkylphenyl group the optionally substitutable.

As aryl group of Ar (1), you can list those which are similar to aryl group in X which is mentioned earlier.

In General Formula (1), as embodiment of aryl group of Ar', you can list those which are similar to aryl group in X which is mentioned earlier.


{0018}

n is integer 1 - 3.

In addition, when n is 2 or more, inside []

{Chemical Formula 7 }

Being same, differing, it is possible to be.



【0019】

前記X、Ar及びAr'が示す基における置換基としては、ハロゲン原子、ヒドロキシル基、ニトロ基、シアノ基、アルキル基、アリール基、シクロアルキル基、アルコキシ基、芳香族複素環基、アラルキル基、アリールオキシ基、アリールチオ基、アルコキシカルボニル基、又はカルボキシル基などが挙げられる。

【0020】

本発明の一般式(1)で表される有機EL素子用発光材料の具体例を以下に示すが、これら例示化合物に限定されるものではない。

{0019}

You can list halogen atom, hydroxyl group, nitro group, cyano group, alkyl group, aryl group, cycloalkyl group, alkoxy group, heteroaromatic group, aralkyl group, aryloxy group, aryl thio group, alkoxy carbonyl group, or carboxyl group etc as substituent in the aforementioned X, Ar and basis which Ar' shows.

{0020}

embodiment of light-emitting material for organic EL device which is displayed with General Formula (1) of this invention is shown below, but it is not something which is limited in

示化合物に限定されるものではない。
なお、Meはメチル基を示す。

【化8】

【0021】


these example compound.

Furthermore, Me shows methyl group.


{Chemical Formula 8 }

{0021}


AN1




AN2



AN3



AN4




【化9】

【0022】


{Chemical Formula 9 }

{0022}


AN5




AN6




AN7




AN8




AN9




AN10



AN11



AN12



JP2004059535A

2004-02-26


【化10】

{Chemical Formula 10 }


【0023】

{0023}


AN13




AN14




AN15




AN16



AN17



AN18



JP2004059535A


2004-02-26

【化11】

{Chemical Formula 11 }

【0024】

{0024}



JP2004059535A

2004-02-26


【化12】

{Chemical Formula 1 2 }


【0025】

{0025}


AN26




AN27




AN28




AN29




AN30




AN31



AN32



AN33




【化13】

【0026】

{Chemical Formula 13 }

{0026}



本発明の有機EL素子用発光材料は、前記一般式(1)で表されるアントラセン誘導体からなる。

本発明の有機EL素子は、陰極と陽極間に少なくとも発光層を含む一層又は複数層からなる有機薄膜層が挟持されている有機EL素子において、該有機薄膜層の少なくとも1層が、前記有機EL素子用発光材料を単独もしくは混合物の成分として含有する。

前記有機薄膜層が、電子輸送層及び／又は正孔輸送層を有し、該電子輸送層及び／又は正孔輸送層が、前記有機EL素子用発光材料を単独もしくは混合物の成分として含有すると好ましい。


【0027】

また、本発明の有機EL素子は、前記発光層が、さらにアリアルアミン化合物及び／又はスチリルアミン化合物を含有すると好ましい。

スチリルアミン化合物としては、下記一般式(2)で表されるものが好ましい。

【化14】

【0028】



light-emitting material for organic EL device of this invention consists of anthracene derivative which is displayed with aforementioned General Formula (1).

said organic thin film layer at least 1 layer, contains light-emitting material for aforementioned organic EL device as for organic EL device of this invention, organic thin film layer which consists of the one layer or multiple layers which at least includes light emitting layer between cathode and the anode in organic EL device which clamping is done, as component of alone or mixture.

When as component of alone or mixture, aforementioned organic thin film layer, has the electron transporting layer and/or hole transporting layer, said electron transporting layer and/or hole transporting layer, contains light-emitting material for aforementioned organic EL device it is desirable.

{0027}

In addition, organic EL device of this invention, when aforementioned light emitting layer, furthermore contains aryl amine compound and/or styryl amine compound, is desirable.

As styryl amine compound, those which are displayed with below-mentioned General Formula (2) are desirable.

{Chemical Formula 14 }

{0028}


(式中、Ar(2)は、フェニル基、ビフェニル基、ターフェニル基、スチルベン基、ジスチリルアリール基から選ばれる基であり、Ar(3)及びAr(4)は、それぞれ水素原子又は炭素数が6~20の芳香族基であり、Ar(2)、Ar(3)及びAr(4)は置換されてもよい。mは1~4の整数である。さらに好ましくはAr(3)又はAr(4)の少なくとも一方はスチリル基で置換されている。)ここで、炭素数が6~20の芳香族基としては、フェニル基、ナフチル基、アントラニル基、フェナンスリル基、ターフェニル基等が挙げられる。

【0029】

アリールアミン化合物としては、下記一般式(3)で表されるものが好ましい。

【化15】

(式中、Ar(5)~Ar(7)は、置換もしくは無置換の核炭素数5~40のアリール基である。pは1~4の整数である。)



【0030】

ここで、核炭素数が5~40のアリール基としては、例えば、フェニル基、ナフチル基、アントラニル基、フェナンスリル基、ピレニル基、コロニル基、ビフェニル基、ターフェニル基、ピローリル基、フラニル基、チオフェニル基、ベンゾチオフェニル基、オキサジアゾリル基、ジフェニルアントラニル基、インドリル基、カルバゾリル基、ピリジル基、ベンゾキノリル基、フルオランテニル基、アセナフトフルオランテニル基、スチルベン基等が挙げられる。

なお、このアリール基の好ましい置換基としては、炭素数1~6のアルキル基(エチル基、メチル基、i-プロピル基、n-プロピル基、s-ブチル基、t-ブチル基、ペンチル基、ヘキシル基、シクロペンチル基、シクロヘキシル基等)、炭素数1~6のアルコキシ基(エトキシ基、メトキシ基、i-プロポキシ基、n-プロポキシ基、s-ブトキシ基、t-ブトキシ基、ペントキシ基、ヘキシルオキシ基、シクロペントキシ基、シクロヘキシルオキシ基等)、核原子数5~40のアリール基、核原子数5~40のアリール基で置換されたアミノ基、核原子数5~40のアリール基を有するエステル基、炭素数1~6のアルキル基を有

(In Formula, as for Ar (2), phenyl group, biphenyl group, terphenyl group, stilbene basis, with group which is chosen from di styryl aryl group, Ar (3) and as for Ar (4), the respective hydrogen atom or carbon number may be to be substituted with aromatic group 6 -20, Ar (2), Ar (3) and as for Ar (4). m is integer 1 - 4. Furthermore preferably Ar (3) or at least one of Ar (4) is substituted with styryl group.) Here, carbon number you can list phenyl group, naphthyl group, anthranyl group, phenanthryl group, terphenyl group etc as aromatic group 6 - 20.

{0029}

As aryl amine compound, those which are displayed with below-mentioned general formula (3) are desirable.

{Chemical Formula 1 5 }

(In Formula, Ar (5) - Ar (7) is aryl group of substituted or unsubstituted nucleus carbon number 5~40. p is integer 1 - 4.)

{0030}

Here, nucleus carbon number you can list for example phenyl group, naphthyl group, anthranyl group, phenanthryl group, pyrenyl group, coronyl group, biphenyl group, terphenyl group, pillow jp9 jp11 basis, furanyl group, thiophenyl basis, benzo thiophenyl basis, oxadiazolyl group, biphenyl anthranyl group, indolyl group, carbozolyl group, pyridyl group, benzo quinolyl group, fluoranthenyl basis, acenaphtho fluoranthenyl basis and stilbene basis etc as aryl group 5 - 40.

Furthermore, carbon number 1 to 6 alkyl group (ethyl group, methyl group, i - propyl group, n - propyl group, s - butyl group, t-butyl group, pentyl group, hexyl group, cyclopentyl group, cyclohexyl group etc), carbon number 1 to 6 alkoxy group (ethoxy group, methoxy group, i - propoxy group, n - propoxy group, s - butoxy group, t - butoxy group, pentoxy group, hexyloxy group, cyclopentoxy group, cyclohexyloxy group etc), you can list ester group, cyano group, nitro group, halogen atom etc which possesses ester group, carbon number 1 to 6 alkyl group which possesses aryl group of amino group, nucleus number of atoms 5~40 which is substituted with aryl group of aryl group, nucleus number of atoms 5~40 of nucleus number of

するエステル基、シアノ基、ニトロ基、ハロゲン原子等が挙げられる。

【0031】

以下、本発明の有機EL素子の素子構成について説明する。

本発明の有機EL素子の代表的な素子構成としては、(1)陽極／発光層／陰極(2)陽極／正孔注入層／発光層／陰極(3)陽極／発光層／電子注入層／陰極(4)陽極／正孔注入層／発光層／電子注入層／陰極(5)陽極／有機半導体層／発光層／陰極(6)陽極／有機半導体層／電子障壁層／発光層／陰極(7)陽極／有機半導体層／発光層／付着改善層／陰極(8)陽極／正孔注入層／正孔輸送層／発光層／電子注入層／陰極(9)陽極／絶縁層／発光層／絶縁層／陰極(10)陽極／無機半導体層／絶縁層／発光層／絶縁層／陰極(11)陽極／有機半導体層／絶縁層／発光層／絶縁層／陰極(12)陽極／絶縁層／正孔注入層／正孔輸送層／発光層／絶縁層／陰極(13)陽極／絶縁層／正孔注入層／正孔輸送層／発光層／電子注入層／陰極などの構造を挙げることができる。

これらの中で通常(8)の構成が好ましく用いられるが、もちろんこれらに限定されるものではない。

この有機EL素子は、通常透光性の基板上に作製する。

この透光性基板は有機EL素子を支持する基板であり、その透光性については、400～700nmの可視領域の光の透過率が50%以上であるものが望ましく、さらに平滑な基板を用いるのが好ましい。

【0032】

このような透光性基板としては、例えば、ガラス板、合成樹脂板などが好適に用いられる。

ガラス板としては、特にソーダ石灰ガラス、バリウム・ストロンチウム含有ガラス、鉛ガラス、アルミノケイ酸ガラス、ホウケイ酸ガラス、バリウムホウケイ酸ガラス、石英などで成形された板が挙げられる。

また、合成樹脂板としては、ポリカーボネート樹脂、アクリル樹脂、ポリエチレンテレフタレート

atoms 5~40 as substituent where this aryl group is desirable.

{0031}

You explain below, concerning element configuration of organic EL device of this invention.

As representative element configuration of organic EL device of this invention, (1) anode/light emitting layer/cathode (2) anode/hole injection layer/light emitting layer/cathode (3) anode/light emitting layer/electron-injecting layer/cathode (4) anode/hole injection layer/light emitting layer/electron-injecting layer/cathode (5) anode/organic semiconductor layer/light emitting layer/cathode (6) anode/organic semiconductor layer/electron barrier layer/light emitting layer/cathode (7) anode/organic semiconductor layer/light emitting layer/ deposit improvement layer /cathode (8) anode/hole injection layer/hole transporting layer/light emitting layer/electron-injecting layer/cathode (9) anode/insulating layer/light emitting layer/insulating layer/cathode (10) anode/inorganic semiconductor layer/insulating layer/light emitting layer/insulating layer/cathode (11) anode/organic semiconductor layer/insulating layer/light emitting layer/insulating layer/cathode (12) anode/insulating layer/hole injection layer/hole transporting layer/light emitting layer/insulating layer/cathode (13) anode/insulating layer/hole injection layer/hole transporting layer/light emitting layer/electron-injecting layer/cathode or other structure can be listed.

It can use configuration of (8) usually desirably among these, but it is not something which is limited of course in these.

It produces this organic EL device, usually on substrate of translucent.

As for this transparent substrate with substrate which supports organic EL device, those where transmittance of light of visible region of 400 - 700 nm is 50% or higher concerning translucent, are desirable, furthermore it is desirable to use smooth substrate.

{0032}

As this kind of transparent substrate, it can use for ideal for example glass sheet, synthetic resin sheet etc.

As glass sheet, you can list sheet which formed with especially soda lime glass, barium * strontium content glass, lead glass, aluminosilicate glass, borosilicate glass, barium borosilicate glass, quartz etc.

In addition, polycarbonate resin, acrylic resin, polyethylene terephthalate resin, polyether sulfide resin,

樹脂、ポリエーテルサルファイド樹脂、ポリサルフォン樹脂などの板が挙げられる。

次に、上記の陽極としては、仕事関数の大きい(4eV以上)金属、合金、電気伝導性化合物又はこれらの混合物を電極物質とするものが好ましく用いられる。

このような電極物質の具体例としては、Auなどの金属、CuI, ITO(インジウムチンオキサイド), SnO_2 , ZnO , In-Zn-O などの導電性材料が挙げられる。

この陽極を形成するには、これらの電極物質を、蒸着法やスパッタリング法等の方法で薄膜を形成させることができる。

この陽極は、上記発光層からの発光を陽極から取り出す場合、陽極の発光に対する透過率が10%より大きくなるような特性を有していることが望ましい。

また、陽極のシート抵抗は、数百 Ω/\square 以下のものが好ましい。

さらに、陽極の膜厚は、材料にもよるが通常10nm~1 μm 、好ましくは10~200nmの範囲で選択される。

{0033}

次に、陰極としては、仕事関数の小さい(4eV以下)金属、合金、電気伝導性化合物及びこれらの混合物を電極物質とするものが用いられる。

このような電極物質の具体例としては、ナトリウム、ナトリウム-カリウム合金、マグネシウム、リチウム、マグネシウム-銀合金、アルミニウム/酸化アルミニウム、 $\text{Al/Li}_2\text{O}$, Al/LiO_2 , Al/LiF , アルミニウム-リチウム合金、インジウム、希土類金属などが挙げられる。

この陰極はこれらの電極物質を蒸着やスパッタリング等の方法により薄膜を形成させることにより、作製することができる。

ここで、発光層からの発光を陰極から取り出す場合、陰極の発光に対する透過率は10%より大きくすることが好ましい。

また、陰極としてのシート抵抗は数百 Ω/\square 以下が好ましく、さらに、膜厚は通常10nm~1 μm 、好ましくは50~200nmである。

{0034}

本発明の有機EL素子においては、このようにして作製された一対の電極の少なくとも一方の表面に、カルコゲナイド層、ハロゲン化金属層又

polysulfone resin or other sheet it is listed as synthetic resin sheet.

Next, it can use those which designate (4 eV or more) metal, alloy, electrically conductive compound or these mixture where work function is large as above-mentioned anode, as electrode substance desirably.

As embodiment of this kind of electrode substance, Au or other metal, Cu I, ITO (indium chin oxide), SnO_2 , you can list ZnO , In-Zn-O or other electrically conductive material.

This anode is formed, these electrode substance, thin film can be formed with the vapor deposition method and sputtering method or other method.

This anode, when light emitting from above-mentioned light emitting layer is removed from anode, has had kind of characteristic where transmittance for the light emitting of anode 10% compared to becomes large, it is desirable.

In addition, as for sheet resistance of anode, those of several hundred : Ω/square or below are desirable.

Furthermore, film thickness of anode depends on also material, but it is selected in range of usually 10 nm~1 μm , preferably 10~200 nm.

{0033}

Next, it can use (4 eV or less) metal, alloy, electrically conductive compound where work function is small as cathode, and those which designate these mixture as electrode substance.

As embodiment of this kind of electrode substance, sodium, sodium - potassium alloy, magnesium, lithium, magnesium * silver alloy, aluminum/aluminum oxide, $\text{Al/Li}_2\text{O}$, Al/LiO_2 , you can list Al/LiF , aluminum * lithium alloy, indium, rare earth metal etc.

This cathode can produce these electrode substance by forming thin film with vapor deposition and sputtering or other method.

When here, light emitting from light emitting layer is removed from cathode, it enlarges transmittance for light emitting of cathode than 10% it is desirable.

In addition, sheet resistance as cathode several hundred : Ω/square or below is desirable, furthermore, film thickness is usually 10 nm~1 μm , preferably 50~200 nm.

{0034}

Regarding organic EL device of this invention, in surface of at least one of the pair of electrodes which is produced in this way, it is desirable to arrange chalcogenide layer, metal halide

は金属酸化物層(以下、これらを表面層ということがある。)を配置するのが好ましい。

具体的には、発光層側の陽極表面にケイ素やアルミニウムなどの金属のカルコゲナイド(酸化物を含む)層を、また、発光層側の陰極表面にハロゲン化金属層又は金属酸化物層を配置するのがよい。

これにより、駆動の安定化を図ることができる。

【0035】

上記カルコゲナイドとしては、例えば SiO_x ($1 \leq x \leq 2$), AlO_x ($1 \leq x \leq 1.5$), SiON , SiAlON などが好ましく挙げられ、ハロゲン化金属としては、例えば LiF , MgF_2 , CaF_2 , フッ化希土類金属などが好ましく挙げられ、金属酸化物としては、例えば Cs_2O , Li_2O , MgO , SrO , BaO , CaO などが好ましく挙げられる。

【0036】

さらに、本発明の有機EL素子においては、このようにして作製された一対の電極の少なくとも一方の表面に電子伝達化合物と還元性ドーパントの混合領域又は正孔伝達化合物と酸化性ドーパントの混合領域を配置するのも好ましい。

このようにすると、電子伝達化合物が還元され、アニオンとなり混合領域がより発光層に電子を注入、伝達しやすくなる。

また、正孔伝達化合物は酸化され、カチオンとなり混合領域がより発光層に正孔を注入、伝達しやすくなる。

好ましい酸化性ドーパントとしては、各種ルイス酸やアクセプター化合物がある。

好ましい還元性ドーパントとしては、アルカリ金属、アルカリ金属化合物、アルカリ土類金属、希土類金属及びこれらの化合物がある。

本発明の有機EL素子においては、発光層は、
▲1▼注入機能：電界印加時に陽極又は正孔注入層より正孔を注入することができ、陰極又は電子注入層より電子を注入することができる機能
▲2▼輸送機能：注入した電荷(電子と正孔)を電界の力で移動させる機能
▲3▼発光機能：電子と正孔の再結合の場を提供し、これを発光につなげる機能を有する。

【0037】

この発光層を形成する方法としては、例えば蒸

layer or metal oxide layer (Below, these are called surface layer, is.).

Concrete, on anode surface of light emitting layer side chalcogenide (oxide is included.) layer of the silicon and aluminum or other metal, in addition, it is good to arrange metal halide layer or metal oxide layer on cathode surface of light emitting layer side.

Because of this, stabilization of drive is assured, it is possible.

{0035}

As above-mentioned chalcogenide, for example SiO_x ($1 \leq x \leq 2$), AlO_x ($1 \leq x \leq 1.5$), you can list SiON , SiAlON etc desirably, for example LiF , MgF_2 , CaF_2 , you can list the rare earth fluoride metal etc desirably as metal halide, you can list for example Cs_2O , Li_2O , MgO , SrO , BaO , CaO etc desirably as metal oxide.

{0036}

Furthermore, regarding organic EL device of this invention, electron transport chemical compound and also it is desirable in surface of at least one of the pair of electrodes which is produced in this way to arrange mixing area or positive hole-conducting compound and oxidative dopant of reductivity dopant mixing area.

When it makes this way, electron transport chemical compound anion become from mixing area to light emitting layer fill and transmit electron becomes easy to be reduced.

In addition, positive hole-conducting compound oxidation cation become from mixing area to light emitting layer fill and transmit positive hole becomes easy to be done.

As desirable oxidative dopant, there is various Lewis acid and a acceptor compound.

As desirable reductivity dopant, alkali metal, alkali metal chemical compound, there is a alkaline earth metal, rare earth metal and these compound.

Regarding organic EL device of this invention, *1 *injection function; electric field imparting time fills positive hole from anode or hole injection layer be able to do light emitting layer, function which can fill electron & 2 *transport function; which function which move the charge (electron and positive hole) which was filled by power of electric field & 3 *light emission function; electron and the place of recombination of positive hole which are offered from cathode or electron-injecting layer, It possesses function which can connect this to light emitting.

{0037}

for example vapor deposition method, spin coating method,